


**AMENDMENTS TO THE CLAIMS**

**This listing of claims will replace all prior versions and listings of claims in the application:**

**LISTING OF CLAIMS:**

1. (original): A curable composition

which comprises an organic polymer (A) containing reactive silyl groups represented by the general formula (1) given below wherein a is 3 and an organic polymer (B) containing an average of 0.5 to 1.5 reactive silyl groups represented by the general formula (1) given below per molecule.



[wherein  $\text{R}^1$  represents an alkyl group containing 1 to 20 carbon atoms, an aryl group containing 6 to 20 carbon atoms, an aralkyl group containing 7 to 20 carbon atoms or a triorganosiloxy group represented by  $(\text{R}')_3\text{SiO}-$  (in which the three  $\text{R}'$  groups may be the same or different and each represents a monovalent hydrocarbon group containing 1 to 20 carbon atoms) and, when there are two or more  $\text{R}^1$  groups, they may be the same or different, and X represents a hydroxyl group or a hydrolysable group and, when there are two or more X groups, they may be the same or different, and a represents 1, 2 or 3].

2. (original): The curable composition according to Claim 1

wherein the reactive silyl group in the organic polymer (B) is a reactive silyl group represented by the general formula (1) in which a is 2.

3. (original): The curable composition according to Claim 1  
wherein the reactive silyl group in the organic polymer (B) is a reactive silyl group represented by the general formula (1) in which a is 3.
4. (previously presented): The curable composition according to Claim 1  
wherein the organic polymer (B) is a polymer obtained by reacting the above-mentioned organic polymer with a compound containing both a functional group capable of reacting with the reactive group in the above-mentioned organic polymer and a reactive silyl group represented by the general formula (1) in a compound-to-polymer mole ratio of not lower than 0.5 and not higher than 1.5.
5. (previously presented): The curable composition according to Claim 1  
wherein the main chain of each of the organic polymers (A) and (B) is an oxyalkylene polymer.
6. (previously presented): The curable composition according to Claim 1  
wherein the organic polymer (B) contains substantially one reactive silyl group represented by the general formula (1) per molecule.
7. (previously presented): The curable composition according to Claim 1  
wherein the organic polymer (B) has a molecular weight of not higher than 8,000.

8. (previously presented): The curable composition according to Claim 1 wherein the organic polymer (B) contains no urethane bond or urea bond within the molecule.

9. (previously presented): The curable composition according to Claim 1 wherein the organic polymer (A) contains no urethane bond or urea bond within the molecule.

10. (previously presented): The curable composition according to Claim 1 wherein the molecular weight of the organic polymer (B) is lower than the molecular weight of the organic polymer (A) by not less than 1,000.

11. (previously presented): The curable composition according to Claim 2 wherein the organic polymer (B) is a polymer obtained by reacting the above-mentioned organic polymer with a compound containing both a functional group capable of reacting with the reactive group in the above-mentioned organic polymer and a reactive silyl group represented by the general formula (1) in a compound-to-polymer mole ratio of not lower than 0.5 and not higher than 1.5.

12. (previously presented): The curable composition according to Claim 3 wherein the organic polymer (B) is a polymer obtained by reacting the above-mentioned organic polymer with a compound containing both a functional group capable of reacting with the reactive group in the above-mentioned organic polymer and a reactive silyl group represented

by the general formula (1) in a compound-to-polymer mole ratio of not lower than 0.5 and not higher than 1.5.

13. (previously presented): The curable composition according to Claim 2 wherein the main chain of each of the organic polymers (A) and (B) is an oxyalkylene polymer.

14. (previously presented): The curable composition according to Claim 3 wherein the main chain of each of the organic polymers (A) and (B) is an oxyalkylene polymer.

15. (previously presented): The curable composition according to Claim 4 wherein the main chain of each of the organic polymers (A) and (B) is an oxyalkylene polymer.

16. (previously presented): The curable composition according to Claim 2 wherein the organic polymer (B) contains substantially one reactive silyl group represented by the general formula (1) per molecule.

17. (previously presented): The curable composition according to Claim 3 wherein the organic polymer (B) contains substantially one reactive silyl group represented by the general formula (1) per molecule.

18. (previously presented): The curable composition according to Claim 4  
wherein the organic polymer (B) contains substantially one reactive silyl group  
represented by the general formula (1) per molecule.

19. (previously presented): The curable composition according to Claim 5  
wherein the organic polymer (B) contains substantially one reactive silyl group  
represented by the general formula (1) per molecule.

20. (previously presented): The curable composition according to Claim 2  
wherein the organic polymer (B) has a molecular weight of not higher than 8,000.

21. (new): The curable composition according to Claim 1  
wherein the organic polymer (A) has a number average molecular weight of 10,000 to  
17,000,  
the organic polymer (B) has a number average molecular weight of 350 to 11,000, and  
the molecular weight of the organic polymer (B) is lower than the molecular weight of  
the organic polymer (A) by not less than 1,000.

22. (new): The curable composition according to Claim 1  
wherein the organic polymer (B) contains an average of 0.5 to 1.0 reactive silyl groups  
represented by the general formula (1) per molecule.

23. (new): The curable composition according to Claim 1  
wherein the organic polymer (B) contains an average of 0.5 to 0.9 reactive silyl groups  
represented by the general formula (1) per molecule.